

Soudafoam Gap Fill

SODDAL

- High Expanding Gun Foam
- Excellent Filling Characteristics
- Excellent Adhesion to All Building Materials (except PE, PP and PTFE)
- Very High Insulation Values, Both Thermal and Acoustical
- Easy Application
- Excellent Form Stability - No Shrink, No Post Expansion
- No Shrinkage
- CFC Propellants Free - Harmless to Ozone Layer



**Filling of Cavities
Seals Openings & Gaps
Creates Acoustic Screen**

This information and all further technical advice are based on SODDAL present knowledge and experience. However, SODDAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SODDAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SODDAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SODDAL reserves the right to make any changes according to technological progress or further developments.

Soudafoam Gap Fill

SOUDAL

| | |
|-----------------------------------|---|
| Base | Polyurethane |
| Consistency | Stable foam (does not sag) |
| Curing system | Moisture-cure |
| Skin Formation (68°F at 60% R.H.) | Approx. 10 minutes |
| Drying time | Approx. 90min - 1.2 inch foam bead (68°F/65% R.H.) |
| Curing rate (68°F/65% R.H.) | 1 hour for a 1/8" bead |
| Shrink | <7% |
| Post expansion | None |
| Cellular structure | Ca 70-80% closed cells |
| Specific gravity | Ca. 1.62lb/ft ³ (extruded, fully cured) |
| Temperature resistance | -40°F until +194°F when cured Short term (up to 1 hour) 248°F |
| Color | Champagne |
| Fire Class | B3 (DIN4102 part2) |
| Water Absorption | 1% Vol. (DIN53422) |
| Insulation Factor: R-value | 4.0 for 1 inch |
| Pressure Strength | Ca. 4.3 psi |
| Bowing Strength | Ca. 8.6 psi |
| Shear Strength | Ca. 20psi |

(*) These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

Limitations:

- Excellent adhesion on most substrates, except for PTFE, PE and PP.
- Always store can with the valve pointed upwards.
- Cured PU foam must be protected from UV radiation.
- Lower temperature and humidity will extend curing time.

CAUTION:

KEEP OUT OF REACH OF CHILDREN. For professional use only. KEEP AWAY FROM HEAT (>49°F), SPARKS AND OPEN FLAME. DO NOT PUNCTURE OR INCINERATE CAN. DO NOT EXPOSE TO DIRECT SUNLIGHT. USE ONLY IN WELL VENTILATED AREAS. In case of eye contact, flush eye with water for 15 minutes and get immediate medical attention. For inhalation, move to fresh air. For skin contact, wash thoroughly with water and soap. If swallowed, drink large quantities of water, but do not induce vomiting. Call a physician immediately. Refer to SDS for further information.

PLEASE REFER TO TECHNICAL DATA SHEET FOR COMPLETE INFORMATION ABOUT THE PRODUCT



Distributed by: Soudal Accumetric • 350 Ring Road, Elizabethtown, KY 42701 • info@soudalusa.com • 877-873-8739 • www.soudalusa.com

SoudafoamGapFill.Combo/022421