

SILICONE SEALANT – INDUSTRIAL GRADE PART NOS. 143381, 143384, 143387, 143403

TYPICAL PROPERTIES

Uncured

Type One-Part Silicone Rubber
 Physical Form..... Non-Slumping Paste
 Colors..... Clear, Aluminum, White, Black
 Specific Gravity @ 77°F (25°C)..... 1.02
 Extrusion Rate (1/8" orifice, 90 psi), gms/min..... 400
 Flow Rate (sag or slump
 on 1/8" X 4" bead), in. NIL
 Tack-Free Time @ 77°F (25°C) and
 50% RH, min 10-20
 Cure Time @ 77°F (25°C) and 50% RH
 (1/8" thick), hrs..... 24

Cured – Physical

ASTM D 676 Durometer Hardness,
 Shore A, points 24
 ASTM D 412 Tensile Strength, psi (MPa) 350
 ASTM D 412 Elongation, % 500
 ASTM D 746 Brittle Point, degrees ..-100°F (-73°C)
 ASTM D 2137A Volume Coefficient of Thermal
 Expansion, 32°F to 212°F..... 9.3×10^{-4}
 Thermal Conductivity, cal/(cm
 (degree C), (sec) 0.45×10^{-3}
 BTU per (ft) (degrees F) (hr.) 0.11
 Service Temperature..... -40°F to 400°F
 Application Temperature -35°F to 140°F



FEATURES

- Bonds and seals
- Insulates thermally and electrically
- Forms a waterproof and weatherproof seal
- Adheres to clean metal, glass most types of wood, silicone resin, synthetic fiber, painted surfaces and much more....
- Good resistance to weathering, vibration, moisture, ozone and extreme temperatures

TYPICAL APPLICATIONS

- Adhering auto and appliance trim, including metal, fabric and fabric-backed plastics
- Bonding gaskets in heating and refrigeration units
- Attaching screwless brackets or nameplates and tacking plastic materials to metal
- Sealing windows in oven doors and flues on gas appliances, flanged pipe joints, access doors
- Providing forming-in-place gaskets for gear boxes, compressors, pumps
- Bonding and sealing appliance parts
- Bonding signs and sign letters
- Creating anti-abrasion coatings
- Sealing marine cabins, windows and more...

Packaging

Colors: Clear, Aluminum, White, Black
 Size: 300ml Cartridge

DESCRIPTION

Dynatex® Silicone Sealant - Industrial Grade is a paste-like, one component material which cures to a tough, rubbery solid upon exposure to moisture in the air. Because it does not flow due to its own weight, this sealant can be applied overhead or on sidewall joints and surfaces without sagging, slumping or running off. It may be applied in sub-zero weather without loss of extrusion or physical property characteristics. Fully cured **Dynatex® Silicone Sealant - Industrial Grade** can be used for extended periods at temperatures up to 450°F (232°C), and for shorter periods as high as 500°F (260°C). Test have shown that even after two months at 450°F (232°C), or up to one week at 500°F (260°C), the sealant remains rubbery.

HOW TO USE

Dynatex® Silicone Sealant - Industrial Grade is supplied in ready-to-use form. It flows readily from its container under pressure. A spatula or wooden paddle can be used to tool the surface.

Cure progresses inward from the surface. At conditions of 75°F (24°C) and 50-percent relative humidity, a tack-free skin forms within 20 minutes. Tooling should be completed within 5 to 10 minutes of application. Alternate periods of application and tooling may be required. If masking tape is used to mask an area it must be removed before the tack-free skin forms.

CURE TIME

Cure time is affected by relative humidity, degree of confinement and cross-sectional thickness of the sealant. Sections up to 1/8-inch thick become rubbery solids in about 24 hours at room temperature at 20-percent relative humidity. Less moisture content reduces cure time slightly. In 24 hours, sections up to 1/8-inch thick cure to a rubber with a Shore A Durometer hardness of about 20 points. After 3 days at room temperature, this Durometer Hardness levels off to about 25 points.

In applications where **Dynatex® Silicone Sealant - Industrial Grade** may be partially or totally confined during cure, the time required for proper cure is generally lengthened by the degree of confinement. It is possible that with absolute confinement cure will not be completed. The result is the softening of the sealant at elevated temperatures.

Metal-to-metal bonds should not overlap more than one inch. Every application involving confinement during cure should be thoroughly tested before commercialization.

Curing time increases with the thickness of the sealant. A 1/2-inch cross section, for example, may require 3 or 4 days for complete solidification. However, the cure will have penetrated the outer 1/8-inch in about 24 hours.

Adhered to glass, metal or most woods, **Dynatex® Silicone Sealant - Industrial Grade** has typical peel strength of 20 pounds per inch, after 72 hours at room temperature.

An odor caused by the liberation of acetic acid is given off during cure. This odor disappears as the cure progresses and is not detectable after cure is complete. Fully cured sealant is non-hazardous.

SPECIFICATIONS

Dynatex® Silicone Sealant - Industrial Grade meets performance requirements for the following:

FDA/USDA requirements for use in establishments operating under Federal Meat and Poultry Inspection Program. When Cured and washed, ingredients remaining, or which could migrate to food are listed on FDA Regulation No. 21 CFR 177.2600. Meets Federal Specifications TT-S-00230C, ASTM C-920 and NSF Standard 51.

STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **Dynatex® Silicone Sealant - Industrial Grade** has a shelf life of 12 months from date of shipment. In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the nozzle tip pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non-warranty: Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted. Suggestions of uses should not be taken as inducements to infringe any patents.

Dynatex® a division of **SOUDAL**

350 Ring Road
Elizabethtown, KY 42701
Email: sales@dynatex.net

Toll Free: (800) 999-2937
Ph: (270) 769-5557
Fax (270) 769-6418

Website: www.dynatex.net