

**TRUCK N' TRAILER FLEXIBLE SEALANT  
PART NOS. 143409, 143410, 143411**

**TYPICAL PROPERTIES**

**Uncured**

Appearance.....Smooth homogenous paste  
 Colors.....Black, White, Grey  
 Specific Gravity .....1.53  
 Tack Free Time, minutes..... 20  
 Extrusion Rate.....400 g/min.

**Cured – Physical**

**7 Days @ 77°F (25°C) and 50% RH  
(1/8" thickness)**

Durometer Shore A Hardness ..... 35 points  
 Tensile Strength..... 180 psi  
 Elongation, percent..... 350  
 Modulus..... 130 psi  
 Shrinkage .....NIL  
 Service Temperature.....-40°F to 200°F  
 Application Temperature ..... -35°F to140°F



**DESCRIPTION**

*Dynatex® Truck N' Trailer Flexible Sealant (GTX seam Sealer)* is an Ultra Synthetic Polymer, designed to resist all the on-the-road flexing and vibration. It cures quickly and provides permanent adhesion with excellent elasticity. It is specially formulated to offer outstanding primer-less adhesion to all basic substrates found in the transportation market, such as steel, aluminum, glass, vinyl and wood. It can be applied and tooled in almost all-weather conditions.

**TYPICAL APPLICATIONS**

Popular applications include:

- Tractor trailers
- RV's
- Buses
- Van conversions
- Shipping containers and many other adhesive /sealant applications
- Metal to metal

**FEATURES**

- Strong heavy-duty multi-purpose adhesive sealant
- Solvent free with no unpleasant odor
- Compatible with most paints\*
- Non-streaking or staining
- Tack-free time 20 minutes
- VOC Compliant

**MEETS**

- ASTM C920, Type S, Grade NS, Class 35, Use T, NT, M, A, G & O.
- Federal Specification TT-S-0230C, Type II, Class A

*\*Always test small area for compatibility before applying.*

**Packaging**

Colors: Black, White, Grey  
 Size: 300ml Cartridge

## STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **Dynatex® Truck N' Trailer Flexible Sealant (GTX seam Sealer)** has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the nozzle tip pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

## USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

**Non-warranty:** Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted.

Suggestions of uses should not be taken as inducements to infringe any patents.



350 Ring Road  
Elizabethtown, KY 42701  
Email: sales@dynatex.net

Toll Free: (800) 999-2937  
Ph: (270) 769-5557  
Fax (270) 769-6418

Website: www.dynatex.net