

Fast Cure Adhesive

TYPICAL PROPERTIES

Appearance	Smooth
Specific Gravity	1.45
Sag/Slump	NIL
Extrusion Rate	250 g/min.
Tack Free Time at 75°F (24°C) and 50% RH	20 min.
Cured-Physical	
Durometer, Shore A Hardness	55 points
Ultimate Tensile Strength	400 psi
Elongation	400%
Modulus	250 psi
Solid	98%
Service Temperature	-40°F to 200°F
Application Temperature	-35°F to 140°F

DESCRIPTION

BOSS® 185 Multi-Seal® Fast Cure Adhesive/Sealant is a one component, high performance adhesive/sealant formulated with USP™ Technology. **BOSS® 185 Multi-Seal®** provides excellent durability, maximum adhesive strength and is VOC compliant in all 50 states. **BOSS® 185 Multi-Seal®** is color stable and UV resistant (non-yellowing) and contains no isocyanates, solvents, halogens or acids. **BOSS® 185 Multi-Seal®** is a moisture curing sealant that remains flexible, even at low temperatures, with quick grab strength and excellent adhesion to various substrates such as aluminum, steel, glass, wood, brick, concrete, mirrors and many plastics.

FEATURES

- VOC Compliant in all 50 states
- Qualifies for LEED Credits
- Immediate high grab strength on nearly all surfaces
- Ease of use, one-part adhesive, no mixing required
- Outstanding bond strength on most surfaces
- Primerless adhesion on most damp & non-porous surfaces
- Good weatherability-virtually unaffected by sunlight, rain, snow, ozone, and temperature extremes
- Good UV resistance and color stability
- Non-yellowing and non-staining
- Non-streaking
- Non-corrosive
- Low odor
- Non-flammable
- Free from solvents and isocyanates
- Paintable with most latex base paints*
- Packaged in all weather plastic cartridges

HOW TO USE

BOSS® 185 Multi-Seal® Fast Cure Adhesive/Sealant is supplied ready to use. Under pressure it flows readily from its container. The paste-like consistency makes it easy to work. A spatula or wooden paddle can be used for tooling the surface. Tooling is not practical after this skin begins forming and should be completed within three to six minutes of application, even though this may require alternate periods of applying and tooling. Likewise, if masking tape has been used to mark off an area, it should be removed before the tack-free skin forms.

Continued...



APPLICATIONS

- Aluminum
- Steel
- Glass
- Wood
- Brick
- Concrete
- Mirrors
- Many plastics

Scan the QR Code to see the full line of **BOSS® PRO** Products!



SPECIFICATIONS

BOSS® 185 Multi-Seal® meets ASTM C920, Type S, Grade NS, Class 25, Use T, NT, M, A, G and O, Federal Specification TT-S-000230C, Type II, Class A.

CLEAN UP

Uncured sealant can be easily removed using BOSS® 335 or a solvent such as alcohol or acetone. For an environmental and health friendlier choice use BOSS® Biggie Wipes. If the sealant is cured it must be removed mechanically by cutting and scraping.

SHIPPING LIMITATIONS

None.

Reactive VOC 20 g/l (<2% wt.)

LIMITATIONS

- Do not use for structural glazing
- Do not use for window glazing
- Not recommended for use on PE, PP or PTFE (Teflon) due to poor adhesion to these substrates
- Poor resistance to solvents, concentrated acids & chlorinated hydrocarbons
- Not recommended for applications below the water line, continuous immersion or for sealing/bonding windshields
- It is the sole responsibility of the user to test the adhesion to the substrate for suitability

CAUTION

DIRECT CONTACT OF UNCURED SEAL-ANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE, AND THROAT. Avoid eye and skin contact. Use only outdoors or in a well ventilated area. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. KEEP OUT OF THE REACH OF CHILDREN. For safe handling information on this product, consult the Safety Data Sheet (SDS).

STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), BOSS® 185 Multi-Seal® Fast Cure Adhesive/ Sealant has a shelf life of 12 months from date of shipment. In countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright with the nozzle tip pointed upwards. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

TECHNICAL DATA SHEET

COLORS

- White

PACKAGING

- 9.5 oz. Cartridges
- Other sizes available upon request

Limited Warranty: Buyer assumes all risks of use, handling and storage of product not in strict accordance with label directions. Liability for any incidental or consequential damage or loss is specifically excluded at all times. Any implied warranty of merchantability or fitness for particular use is excluded. Seller will not accept liability for more than product replacement.



Soudal Accumetric

MADE IN U.S.A.

350 Ring Road
Elizabethtown, KY 42701
800-928-BOSS(2677)
270-769-3385
FAX 270-765-2412
www.bossproducts.com

BOSS is a registered trademark of Soudal