



## SODASIL RTV1

Revision: 06/18/2019

Page 1 of 2

**Technical Data:**

Base	Polysiloxane	
Sag	No sag in vertical displ. @ 120°F	ASTM C 639
Curing system	Moisture Cure	
Skin Formation (*)	5 - 10 minutes	@ 75°F & 50% relative humidity
Tack-free time (*)	10 - 20 minutes	ASTM C 679
Curing time (*)	24 hrs, 1/8" diameter bead	@ 75°F & 50% relative humidity
Hardness – Shore A	30 +/- 5	ASTM C 661
Tensile Yield	350 psi	ASTM D 412
Elongation	500 %	ASTM D 412
Movement capability	+/- 25%	ASTM C 719
Stain and color change	Passes	ASTM C 510 (mortar)
Artificial weathering	No Cracking	ASTM C 793
Service temperature range	-40°F to +400°F	
Application temperature range	-35°F to +140°F	
Shelf life	12 months	Stored between 41°F & 77°F
VOC	30 g/L	

(\*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates. Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

**Product:**

Soudasil RTV1 is a one-part acetoxy silicone sealant used for variety of sealing and gasketing needs.

**Characteristics:**

- Permanent color
- UV resistant
- Stays fully elastic after curing
- Very good adhesion on many materials
- Very easy application
- Typical acetic smell

**Applications:**

- Building and construction joints
- Glazing on aluminum frames
- Sealing cold storage rooms and containers
- Sealing in air conditioning systems
- Window and door joints

**Color:**

Various

**Packaging:**

10.1 fl. oz. cartridges

**Surfaces:**

*Type:* all usual building surfaces

*State of surface:* clean, dry, free of dust and grease

**We recommend a preliminary compatibility test, especially on PVD and powder coated materials.**

**Joint Size:**

Minimum width: 1/4"

Maximum width: 1 3/16"

Minimum Depth: 1/5"

Recommendation: 2 x depth = width

**Application:**

*Method:* Manual or pneumatic caulking gun

*Conditions:* 40° F to 95° F

*Finish:* soapy water before skinning

*Repair With:* Soudasil RTV1

*Clean Up:* white mineral spirit immediately after use

Remark: This information and all further technical advice are based on SODAL present knowledge and experience. However, SODAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SODAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SODAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SODAL reserves the right to make any changes according to technological progress or further developments.

---

## SODASIL RTV1

---

Revision: 06/18/2019

Page 2 of 2

### Shelf life:

12 months in unopened packaging in a cool and dry storage place at temperatures between +41° F and +77° F.

Storage in excessive heat and/or high humidity conditions may reduce shelf life up to 30%

### Remarks:

- Not recommended for use on PC and PMMA because it can cause crazing (stress cracking) in these materials.
- Due to acetic character some metals (copper, lead) can be attacked.
- Contact between this sealant and the primary sealants of double glazed insulation windows or the PVB film of security glass should be avoided.
- Do not use as structural glazing adhesive.
- Contact with plasticizer containing plastics (e.g. flexible PVC, butyl rubber, EPDM,...) can lead to incompatibilities, such as discoloration or loss of adhesion. We recommend a preliminary compatibility test.

### Meets:

ASTM C 920, Type S, Grade NS, Class 25, Use NT, A, G and O\*\*, Federal Specification TT-S-00230C.

\*\* See recommended substrates.

FDA/USDA requirements for use in establishments operating under Federal Meat and Poultry Inspection Program. When cured and washed, ingredients remaining or which could migrate to food are listed on FDA Regulation No. 21 CFR 177.2600

NSF Standard 51

### Health- and Safety Recommendation:

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE AND THROAT. KEEP OUT OF REACH OF CHILDREN. Avoid skin and eye contact. On Contact, uncured sealant could cause irritation to skin and eyes. In case of eye contact, flush eyes with warm water for 15 minutes, call a physician. For skin contact, remove sealant with a paper towel. If swallowed, do not induce vomiting, call a physician. Soudasil RTV1 is manufactured for professional use only. Refer to Material Safety Data Sheet (MSDS) for further information.

### Limited Warranty:

SOULDAL warrants product to be of good quality and will replace or, at our election, refund the purchase price of any products proved to be defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, SOULDAL MAKES NO WARRANTY OR GUARANTEE, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and SOULDAL shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith.

Remark: This information and all further technical advice are based on SOULDAL present knowledge and experience. However, SOULDAL assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, SOULDAL disclaims all WARRANTIES EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. SOULDAL SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. SOULDAL reserves the right to make any changes according to technological progress or further developments.